

Pigment Powder for Coating

Apament®Coat

FullColour	Apament®Coat	C.I.Name	Application							Properties		
			Decorative Paints		IndustrialCoatings					Light fastness FullTone/Tint	Weather fastness Full Tone/Tint	Heat Stability(°C)
			Solvent Base	Water Base	AutomotiveOE M	AutomotiveRe finish	Industrial Paints	Powder Coatings	Coil Coatings			
	Yellow G	Yellow 1	●	●						7/5	—	160°C
	Fast Yellow GRX	Yellow 13	○	○			●	○		6/5	4/3	240°C
	Fast Yellow RN	Yellow 65	●	●						6/5	4/2	160°C
	Yellow 5GSC	Yellow 74	●	●			○			7/5	4/2	180°C
	Yellow HR	Yellow 83	●	●			●	●		7/6	4/3	200°C
	Yellow DS	Yellow 110	●	●	●	●	●	●	○	8/7	5/4	200°C
	Yellow HD	Yellow 138	●	●	○	○	●	●		8/7	5/4	200°C
	Yellow M2R	Yellow 139	●		○	●	●	●		7-8/7	4/3-4	180°C
	Yellow H4G	Yellow 151	●	●	○	○	●	●		8/7	5/4	180°C
	Fast Yellow H3G	Yellow 154	●	●	○	●	●	●		8/7	5/4	160°C
	Fast Orange RN	Orange 5	●	●			●			6/5	5/4	180°C
	Fast Orange G	Orange 13	○	○			●	●		7/6	5/4	220°C
	Orange HL	Orange 36	●	●	○	●	●	●		8/7	5/4	160°C
	Orange GL	Orange 64						●	○	5-6/3	—	180°C
	Red F2R	Red 2	●	●						6/5	4/3	180°C
	Fast Red RN	Red 3	●	●						6/4	5/4	180°C
	Fast Red R	Red 4	●	●						6/3	4/3	160°C
	Red Toner 2B	Red 48:1	○	○			●	●		7/6	5/4	220°C
	Fast Red 2BP	Red 48:2	○	○			●	●		6/5	4/3	260°C
	Fast Red 2BS	Red 48:3	○	○			●	●		7/6	4/3	260°C
	Fast Red FB-2B	Red 48:4	○	○			●	●		8/7	5/4	200°C
	Rubine Red SC	Red 57:1	○	○			●	●		6/5	4/3	260°C
	Red FGR	Red 112	●	●						7-8/4-5	5/4	200°C
	Fast Red SC	Red 122	●	●						8/7	5/4	200°C
	Red F3RK	Red 170	●	●		●	●	●		7/5	4/2	180°C

Pigment Powder for Coating

Apament®Coat

FullColour	Apament®Coat	C.I.Name	Application							Properties		
			Decorative Paints		IndustrialCoatings					Light fastness FullTone/Tint	Weather fastness Full Tone/Tint	Heat Stability(°C)
			Solvent Base	Water Base	AutomotiveOE M	AutomotiveRe finish	Industrial Paints	Powder Coatings	Coil Coatings			
	Fast Red A3B	Red 177			●	●	●	●	○	8/7	5/4	200°C
	Red F6RK	Red 210	●	●	●	●	●	●	●	7/6	5/4	180°C
	Red KA	Red 264		○	●	●	●	●	○	8/8	5/5	200°C
	Red B	Violet 19	●	●	●	●	●	●	●	8/7	5/4	200°C
	Viloet RL	Violet 23	●	●	○	●	●	●	●	8/8	5/4	180°C
	Phthalocyanine Blue BN	Blue 15:0	●	●								
	Alfa Blue	Blue 15:1	●	●	○	●	●	○	●	8/8	5/5	200°C
	Blue BX	Blue 15:2	○	●	●	●	●	●	●	8/8	5/5	200°C
	Phthalocyanine Blue BGS	Blue 15:3	●	●		○	●	○	●	8/8	5/5	200°C
	Phthalocynine Blue Beta Form	Blue 15:4	●	●	●	●	●	○	●	8/8	5/5	200°C
	Green BX	Green 7	●	●	○	●	●	●	●	8/8	5/5	200°C
	Middle Chrome	Yellow 34	●	●	●	●	●	●	●	7/5	4/3	180°C
	Lemon Chrome	Yellow 34	●	●	●	●	●	●	●	7/5	4/3	180°C
	Scarletr Chrome	Red 104	●	●	●	●	●	●	●	6/4	4/3	200°C

- Suitable for Application
- Potential Use